



**YT – YSER Tack**

*Disproportionated Gum Rosin are derivatives of gum rosin obtained by chemical treatment to reduce the Abietic Acid content.*

**□ GENERAL SPECIFICATIONS**

	<b>YT 301</b>	<b>YT 302</b>	<b>YT 303</b>
<b>Acid Number – Spec.</b>	160 max	160 max	160 max
Acid Number – Typical	150	150	150
<b>Melting Point (°C), R&amp;B – Specs</b>	72 – 78	72 – 78	67 – 73
Melting Point (°C) , R&B – Typical	75	75	70
<b>Colour Gardner – Specs</b>	8 max	8 max	8 max
Colour Gardner – Typical	6/7	6/7	6/7
<b>Abietic Acid (%) – Specs</b>	5 max	1 max	0.5 max
Abietic Acid (%) – Typical	3	0.7	0.3

**□ SPECIAL REMARK**

*The standard characteristics of the resin, with regards to the Melting Point and Abietic content, can be adapted, under the limits of our specs, to the special requirements of our customers. Safety Data Sheet and Technical Data Sheet are available under request for each product.*

**□ CHARACTERISTICS**

*Solubility in aromatic and aliphatic solvents  
Total compatibility with natural and synthetic polymers  
Excellent resistance to oxidation*

**□ APPLICATIONS**

*Tackifier for pressure sensitive adhesives  
Pigments  
Manufacture of SBR and other synthetic rubbers*

**□ FORM OF SUPPLY**

*Block, in 240 kg metallic drums  
Road tanks*

The reproduction of this document is completely forbidden

The information in this publication is, to the best of our knowledge, true and accurate, but since the conditions of use are beyond our control, no warranty is given or to be implied in respect of such information. We are, at all times, willing to study customer's specific outlets involving our products in order to enable their most effective use.



***Distributed in the U.S.A. by:***  
***PDM, Inc., 104 Webster Building, 3411 Silverside Road, Wilmington, DE 198104806 • U.S.A.***  
***Toll-Free (800) 288-0768 • Phone (302) 478-0768 • Fax (302) 478-0299 • E-Mail: godon@zdial.com***